

A&J VINEYARD SUPPLY INC.

FLAT ROLLED STEEL THICKNESS CHART

Data Provided By

Western Flat-Rolled Steel & Processing

Hot Rolled & P&O		
Gauge	Thickness	
	Decimal Equiv.	Tolerance Range
7	.1793	.1873
		.1713
8	.1644	.1724
		.1564
9	.1495	.1575
		.1415
10	.1345	.1425
		.1265
11	.1196	.1276
		.1116
12	.1046	.1126
		.0966
13	.0897	.0967
		.0827
14	.0747	.0817
		.0677
15	.0673	.0733
		.0613
16	.0598	.0658
		.0538

Galvanized		
Gauge	Thickness	
	Decimal Equiv.	Tolerance Range
10	.1382	.1472
		.1292
11	.1233	.1323
		.1143
12	.1084	.1174
		.0994
13	.0934	.1014
		.0854
14	.0785	.0865
		.0705
15	.0710	.0770
		.0650
16	.0635	.0695
		.0575

For additional technical information, call 707.963.5354